

Claim 4, line 1, change "2" to -1--.

Claim 5, line 1, change "2" to -1--.

a2 7(Amended). A print-receptive, pill-resistant, knitted fabric, said fabric knitted from yarn formed from high-tenacity, staple synthetic fiber having a tenacity value of greater than about 4 grams/denier, wherein said knitted fabric has a pilling resistance value of greater than about 3, and said high-tenacity, staple synthetic fiber is selected from the group consisting of air jet spun polyester; nylon; acrylic; and polypropylene and wherein said high-tenacity, staple synthetic fiber has a denier of less than about 1.5.

Claim 10, line 1, change "9" to -7--.

a3 23(Amended). A printed, pill-resistant, article of apparel, said article of apparel knitted from yarn formed from high-tenacity, staple synthetic fiber having a tenacity value of greater than about 4 grams/denier, wherein said article of apparel has a pilling resistance value of greater than about 3 and wherein said knitted fabric is a double-knit fabric having a front side and a back side, the front side being formed from said high-tenacity, staple synthetic fiber and the back side being substantially formed from cellulosic yarn, said cellulosic yarn being selected from the group consisting of cotton and synthetic cellulosic fibers.

24(Amended). A printed, pill-resistant, article of apparel, said article of apparel knitted from yarn formed from high-tenacity, staple synthetic fiber having a tenacity value of greater than about 4 grams/denier, wherein said article of apparel has a pilling resistance value of greater than about 3, and said high-tenacity, staple synthetic fiber is selected from the group consisting of air jet spun polyester; nylon; acrylic; and polypropylene and wherein said high-tenacity, staple synthetic fiber has a denier of less than about 1.5.